



MODENA CENTRO PROVE s.r.l.

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78  
Tel. 059822417 r.a. - Fax 059380281 - e-mail : [info@modenacentroprove.it](mailto:info@modenacentroprove.it) - [www.modenacentroprove.com](http://www.modenacentroprove.com)  
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

## TEST REPORT: 20198604/3

Modena, 11/12/19

<b>CUSTOMER</b>	<b>FLORIM CERAMICHE SPA - - VIA CANALETTO 24 - 41042 - FIORANO MODENESE - MO</b>
<b>MATERIAL and/o SAMPLE to be tested</b>	porcelain tiles;
<b>Denomination</b>	serie Onyx & More articolo White porphyry superficie strutturato spessore 6 mm marchio casa Dolce casa;
<b>Date of sample reception</b>	18/11/2019;
<b>Kind of test executed</b>	Determination of Dynamic Coefficient of Friction (DCOF)
<b>Referring standards</b>	ANSI A326.3-2017
<b>Shifting from standards</b>	No one
<b>Equipment</b>	Tribometer BOT3000E cod. MCP C143
<b>Subcontracted phases</b>	No one
<b>Sampling made by</b>	Customer

*The test results showing in this Report are only referred to the sample taken by our staff or supplied by the Customer. He commits himself to reproduce integrally this document. Partial reproduction is forbidden.  
The times of retain of the samples was indicated in the offer related to the test report.*

**Examiner**  
  
P.I. Fili Thomas

MODENA CENTRO PROVE  
  
Ceramic Dept. Responsible  
P.I. De Pasquale Roberto

MODENA CENTRO PROVE  
  
Director  
Sant'Unione dr. Giuseppe



## DETERMINATION OF DYNAMIC COEFFICIENT OF FRICTION

Beginning date : 11/21/2019

Analysis ending date : 11/21/2019

**SAMPLE** : Ceramic tiles marked « **serie Onyx & More articolo White porphyry superficie strutturato spessore 6 mm marchio casa Dolce casa** »

The test has been carried out using the instrument BOT 3000, tribometer of the coefficient of dynamic friction (DCOF) between a sliding SBR sensor and the surface of test.

### WET OPERATING CONDITION

All test specimens shall be cleaned prior to testing. Place three specimens on a solid surface in a row. Wet the path that the sensor will follow with 0,05% SLS (*Sodium-Lauryl Sulfate*) water.

Make a total of four dynamic measurement on the center tile. Make one measurement then turn the BOT 3000 180° and make the second measurement. Then turn the tile 90° and make the final two measurements in the same fashion above. Record all four dynamic measurements and take an average.

Repeat on other two additional pieces. For textured tile, the three pieces of tile shall be representative of the different texture variations. If the tile is known to have more than three texture variations, test a representative tile of each texture.

### SENSOR VERIFICATION

Values of DCOF on standard tile before testing test specimens	<b>0,28</b>
Values of DCOF on standard tile after testing test specimens	<b>0,28</b>

### RESULTS

Test Condition	Measure 1	Measure 2	Measure 3	Measure 4	Average
Wet DCOF - tile 1	0,45	0,45	0,43	0,43	<b>0,44</b>
Wet DCOF - tile 2	0,45	0,46	0,47	0,45	<b>0,46</b>
Wet DCOF - tile 3	0,47	0,46	0,47	0,47	<b>0,47</b>

### REFERENCE VALUES

ANSI A137.1:2017 prescribe a minimum threshold of 0,42 for level interior spaces expected to be walked upon when wet.

<b>Examiner</b>  P.I. Fili Thomas	MODENA CENTRO PROVE  Ceramic Dept. Responsible P.I. De Pasquale Roberto	MODENA CENTRO PROVE  Director Sant'Unione dr. Giuseppe
---	--	---