

**MODENA CENTRO PROVE s.r.l.**

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78  
Tel. 059 822417 r.a. - Fax 0598635115 - e-mail : [info@modenacentroprove.it](mailto:info@modenacentroprove.it) - [www.modenacentroprove.com](http://www.modenacentroprove.com)  
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

MECCANICA

ECOLOGIA

CERAMICA

AUTOMOTIVE

Modena, 30/10/20

To **FLORIM CERAMICHE SPA**  
VIA CANALETTO 24  
41042 FIORANO MODENESE MO

Attn. **sig. Turrini**

MATERIAL and/or SAMPLE to be tested	Denomination of the Sample	Client Reference – Your delivery	date
porcelain tiles	serie Sensi of Casa dolce casa articolo White Dust naturale spessore 10 mm superficie UGL marchio casa Dolce Casa	ns ritiro	19/10/2020

Here attached, you will receive the Test Report of Serial No. **20206507**/n, which shows the results of tests required.

**MODENA CENTRO PROVE**

MODENA CENTRO PROVE  
  
Director  
Sant'Unione dr. Giuseppe



## TEST REPORT: 20206507/1

Modena, 30/10/20

<b>CUSTOMER</b>	<b>FLORIM CERAMICHE SPA - - VIA CANALETTO 24 - 41042 - FIORANO MODENESE - MO</b>
<b>MATERIAL and/o SAMPLE to be tested</b>	porcelain tiles;
<b>Denomination</b>	serie Sensi of Casa dolce casa articolo White Dust naturale spessore 10 mm superficie UGL marchio casa Dolce Casa;
<b>Date of sample reception</b>	19/10/2020;
<b>Date of sample acceptance</b>	19/10/2020;
<b>Kind of test executed</b>	Determination of the anti-slip property – Walking method – Ramp test
<b>Referring standards</b>	DIN 51130:2014 (Escluso capitoli 4.2 6 Raccolta di volume)
<b>Shifting from standards</b>	No one
<b>Equipment</b>	Pullmeter with ramp cod. MCP C150
<b>Subcontracted phases</b>	No one
<b>Sampling made by</b>	Customer

*The test results reported in this Test Report refer only to the sample sampled by our staff and / or given by the Customer as received.*

*The sample identification data were provided by the customer. Further additional information provided by the Customer will be reported in the Test Report in blue color. If the information provided by the customer influences the validity of the results, MCP declines all responsibility.*

*Any changes / additions made to the Test Report after its first issue will be identified by underlining the text.*

*The Customer undertakes to reproduce this document in its entirety. Any form of partial reproduction is prohibited.*

*The storage times of the samples are indicated on the offer or contract to which this Test Report refers.*

<b>Examiner</b>  p.i. Nassetti Luca	<b>Examiner</b>  p.i. Bortolai Alberto	<b>MODENA CENTRO PROVE</b>  Ceramic Dept. Responsible P.I. De Pasquale Roberto	<b>MODENA CENTRO PROVE</b>  Director Sant'Unione dr. Giuseppe
---	--	---	--



**MODENA CENTRO PROVE s.r.l.**  
 Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78  
 Tel. 059 822417 r.a. - Fax 059380281 - e-mail : [info@modenacentroprove.it](mailto:info@modenacentroprove.it) -  
[www.modenacentroprove.com](http://www.modenacentroprove.com)  
 C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 C.F. e P. IVA n. 01592020364



LAB N°1018L

Membro degli Accordi di Mutuo Riconoscimento EA, IAF e ILAC

Signatory of EA, IAF and ILAC Mutual Recognition Agreements

## DETERMINATION OF THE ANTI-SLIP PROPERTY – WALKING METHOD – RAMP TEST

Beginning date : 19/10/2020

Analysis ending date : 20/10/2020

**SAMPLE** : Ceramic tiles, marked « serie Sensi of Casa dolce casa articolo White Dust naturale spessore 10 mm superficie UGL marchio casa Dolce Casa »





### RESULTS

Mean inclination angle  $\alpha_{ges}$ : 7,4  
 Classification: R9

### CLASSIFICATION

Mean value $\alpha_{ges}$	Class
$6^\circ \leq \alpha_{ges} \leq 10^\circ$	R 9
$10^\circ < \alpha_{ges} \leq 19^\circ$	R 10
$19^\circ < \alpha_{ges} \leq 27^\circ$	R 11
$27^\circ < \alpha_{ges} \leq 35^\circ$	R 12
$\alpha_{ges} > 35^\circ$	R 13

**Note** : The group classification give the parameter for determine the sliding resistance: the group R 9 is less anti-slip, the group R 13 as the maximum effectiveness anti-slip.

<p>Examiner            p.i. Nassetti Luca</p>	<p>Examiner            p.i. Bortolai Alberto</p>	<p>MODENA CENTRO PROVE            Ceramic Dept. Responsible          P.I. De Pasquale Roberto</p>	<p>MODENA CENTRO PROVE            Director          Sant'Unione dr. Giuseppe</p>
---	---	--	---