





















7,00 mm / GLASS

Reference standard	Test method	Reference value	Declared value
 Amount of water absorbed, in percentage	ISO-10545-3	-	< 0,5%
 Resistance to abrasion of glazed tiles	ISO-10545-7	-	4
 Coefficient of thermal linear expansion	ISO-10545-8	-	< 7.5
 Glaze crazing resistance	ISO-10545-11	-	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
 Resistance to high concentrations of acids and alkali	ISO-10545-13	-	UHA - GHA
 Resistance to low concentrations of acids and alkali	ISO-10545-13	-	ULA - GLA
 Resistance to domestic chemicals and additives for swimming pools	ISO-10545-13	-	UA - GA
 Resistance to staining	ISO-10545-14	-	Cl. 5
 Barefoot slip resistance	DIN-51097	-	Cl. C
 Resistance to deep abrasion of unglazed tiles	ISO-10545-6	-	< 300 mm ³

Notes:

Slipperiness test results are referred exclusively to mosaic.

4,50 mm / GLASS

	Reference standard	Test method	Reference value	Declared value
	Amount of water absorbed, in percentage	ISO-10545-3	-	< 0,5%
	Resistance to abrasion of glazed tiles	ISO-10545-7	-	4
	Coefficient of thermal linear expansion	ISO-10545-8	-	< 7.5
	Glaze crazing resistance	ISO-10545-11	-	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Resistance to high concentrations of acids and alkali	ISO-10545-13	-	UHA - GHA
	Resistance to low concentrations of acids and alkali	ISO-10545-13	-	ULA - GLA
	Resistance to domestic chemicals and additives for swimming pools	ISO-10545-13	-	UA - GA
	Resistance to staining	ISO-10545-14	-	Cl. 5
	Barefoot slip resistance	DIN-51097	-	Cl. C
	Resistance to deep abrasion of unglazed tiles	ISO-10545-6	-	< 300 mm ³

Notes:

Slipperiness test results are referred exclusively to mosaic.