



















6,00 mm / FINE PORCELAIN STONEWARE

| | Reference standard E.N. 14411 . Appendix G. Group Bla. UGL | Test method | Reference value | Declared value |
|---|---|--------------|---|---|
|  | Length and width: admitted deviation, in %, of the average size of each tile from the production dimensions | ISO-10545-2 | ±0,6% (±2 mm) | ±0,15% |
|  | Admitted deviation, in %, of the average thickness of each tile from the production dimensions | ISO-10545-2 | ±5% (±0,5 mm) | ±5% |
|  | Maximum straightness deviation, in %, in relation to the corresponding production dimensions | ISO-10545-2 | ±0,5% (±1,5 mm) | ±0,1% |
|  | Maximum right-angle deviation, in %, in relation to the corresponding production dimensions | ISO-10545-2 | ±0,5% (±2 mm) | ±0,2% |
|  | Flatness (centre curvature / edge curvature / warpage) | ISO-10545-2 | ±0,5% (±2mm) | ±0,2% |
|  | Surface quality | ISO-10545-2 | Il 95% min delle piastrelle deve essere esente da difetti visibili / At least 95% of the tiles must be free from visible flaws / 95% min des carreaux ne doivent présenter aucun défaut visible / Mindestens 95% der Fliesen müssen frei von sichtbaren / mín. el 95% de las baldosas tiene que estar exento de defectos visibles | CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / COOTBETCTBYET |
|  | Amount of water absorbed, in percentage | ISO-10545-3 | E<0,5% | average value 0,08% |
|  | Breaking strength in N (thickness < 7,5 mm) | ISO-10545-4 | ≥700 Newton | average value 1350 N* |
|  | Bending strength in N/mm2 | ISO-10545-4 | >35 N/mm2 | average value 52 N/mm2 |
|  | Resistance to deep abrasion of unglazed tiles | ISO-10545-6 | <175 mm3 | average value 140 mm3 |
|  | Thermal shock resistance | ISO-10545-9 | - | RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ |
|  | Frost resistance | ISO-10545-12 | Richiesta / Required / Requisite / Gefordert / Requerida | RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ |
|  | Resistance to staining | ISO-10545-14 | - | Cl. 3-4 |

| | | | | |
|---|---|----------------|---|-----------|
|  | Resistance to low concentrations of acids and alkali | ISO-10545-13 | Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante | ULA |
|  | Resistance to high concentrations of acids and alkali | ISO-10545-13 | Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante | UHA |
|  | Resistance to domestic chemicals and additives for swimming pools | ISO-10545-13 | UB minimo / UB minimum / UB minimum / UB mindestens / UB minimo | UA |
|  | Slip resistance with shoes | DIN-51130:2010 | - | R9 |
|  | Dynamic coefficient of friction (section 9.6 ANSI A 137.1 2012) | DCOF | >0,42 wet | >0,42 wet |

Notes:

For optimal installation results, Florim recommends maintaining a joint of 2 mm 1/12" for single format installations and 3 mm 1/8" to combine mixed formats.

* Test performed on 80x80cm size