



















6,00 mm / FINE PORCELAIN STONEWARE

	Reference standard E.N. 14411 . Appendix G. Group Bla. UGL	Test method	Reference value	Declared value
	Length and width: admitted deviation, in %, of the average size of each tile from the production dimensions	ISO-10545-2	±0,6% (±2 mm)	± 0,15%
	Admitted deviation, in %, of the average thickness of each tile from the production dimensions	ISO-10545-2	±5% (±0,5 mm)	± 5%
	Maximum straightness deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	±0,5% (±1,5 mm)	± 0,1%
	Maximum right-angle deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	±0,5% (±2 mm)	± 0,2%
	Flatness (centre curvature / edge curvature / warpage)	ISO-10545-2	±0,5% (±2mm)	± 0,2%
	Surface quality	ISO-10545-2	Il 95% min delle piastrelle deve essere esente da difetti visibili / At least 95% of the tiles must be free from visible flaws / 95% min des carreaux ne doivent présenter aucun défaut visible / Mindestens 95% der Fliesen müssen frei von sichtbaren / mín. el 95% de las baldosas tiene que estar exento de defectos visibles	CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / COOTBETCTBYET
	Amount of water absorbed, in percentage	ISO-10545-3	E<0,5%	average value 0,08%
	Breaking strength in N (thickness < 7,5 mm)	ISO-10545-4	≥700 Newton	average value 1350 N*
	Bending strength in N/mm2	ISO-10545-4	>35 N/mm2	average value 52 N/mm2
	Resistance to deep abrasion of unglazed tiles	ISO-10545-6	<175 mm3	average value 140 mm3
	Thermal shock resistance	ISO-10545-9	-	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Frost resistance	ISO-10545-12	Richiesta / Required / Requisite / Gefordert / Requerida	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Resistance to staining	ISO-10545-14	-	Cl. 4-5

	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	ULA
	Resistance to high concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	UHA
	Resistance to domestic chemicals and additives for swimming pools	ISO-10545-13	UB minimo / UB minimum / UB minimum / UB mindestens / UB minimo	UA
	Slip resistance with shoes	DIN-51130:2010	-	R9
	Dynamic coefficient of friction (section 9.6 ANSI A 137.1 2012)	DCOF	>0,42 wet	> 0,42 wet

Notes:

* Test performed on 80x80cm size (6mm)