



TEST REPORT
CERAMIC TILES - DETERMINATION OF RESISTANCE TO STAINS
UNI EN ISO 10545-14: 2015

Test report n. 4509/2017 /I
Date of report: 12/11/2017
Customer: FLORIM CERAMICHE S.p.a.
Via Canaletto, 24
41042 FIORANO MODENESE (MO)
Requested on: 12/04/2017
Our ref.number: 21369
Execution place of tests: Scandiano (RE)
Description of the sample: "Ceramic tiles 60x120 cm
marked: Serie Le Veneziane, articolo Santa Croce, superficie lucido,
spessore 10 mm, marchio Cerim""
Sampling: carried out by the customer
Receipt date of samples: 12/05/2017
Execution date of tests: start: 12/06/2017 end: 12/07/2017
Test specification: UNI EN ISO 10545 - 14:2015
Determination of resistance to stains
Warnings: *This test report can not be reproduced in part, without our written consent.
The reported results relate only to the samples tested.
The information included in quotation marks was provided by the customer.*





TEST REPORT

CERAMIC TILES - DETERMINATION OF RESISTANCE TO STAINS

UNI EN ISO 10545-14: 2015

Test report n. 4509/2017 /I

Principle: determination of the resistance to stains by maintaining test solutions and materials in contact with the proper surface of the tiles for a suitable length of time; the surfaces are then subjected to defined cleaning methods, and finally inspected for visual changes.

N. samples tested: 0

Test results:

<u>Staining agents</u>	Sample 1 Class	Sample 2 Class	Sample 3 Class	Sample 4 Class	Sample 5 Class
<u>Stains leaving a trace (pastes)</u>					
Green staining agent in light oil	5	5	5	5	5
<u>Stains having chemical/oxidizing action</u>					
Iodine, alcoholic solution 13 g/l	5	5	5	5	5
<u>Stains forming a film</u>					
Olive oil	5	5	5	5	5

Classification procedure of the test of resistance to stains:

- Class 5: Procedure A, stain removed with warm water (55 ± 5) ° C, allowed to flow for 5 min
- Class 4: Procedure B, stain removed manually using a natural non-abrasive sponge and weak cleaning agent, (pH 6.5÷7.5) (Ajax liquid)
- Class 3: Procedure C, stain removed mechanically for 2 min using a strong cleaning agent containing abrasive (pH 9÷10) (Cif)
- Class 2: Procedure D, stain removed by immersing the sample in a suitable solvent for 24 hours.
- Class 1: stain not removed

End of the document



THE DIRECTOR
 M.L. SIMIONI