



Scandiano, 09/16/2015



Messrs **FLORIM CERAMICHE S.p.a.**

Via Canaletto, 24  
41042 FIORANO MODENESE  
(MO)

**Confidential Test Report N. 3486/2015 /I**  
on ceramic tiles

Our ref.num.: 15437  
Date of request: 09/09/2015

**Test Specimen**

"Panel of dimensions 50 x 100 cm covered with ceramic tiles 60x120 cm  
marked:  
MAPS OF CERIM WHITE NAT 60x120 RET marchio CERIM"

**Source**

Submitted to Laboratory by Client

**Date Received**

09/10/2015

**Time of test execution**

start: 09/16/2015 end: 09/16/2015

**Test detail / method description / test procedure**

" Determination of the anti-slip characteristics -  
Standard DIN 51130:2014 "

*The report relates only to the sample(s) tested. This report must not be reproduced in part  
without the written permission of Main Laboratory Sassuolo, nor used in any way as to lead to  
misrepresentation of the results or their implications.*

Page 1 of 2

Mod. P2321 rev.00



Confidential Test Report N. 3486/2015 /I  
**FLORIM CERAMICHE S.p.a.**

Page 2 of 2

Date 09/16/2015

Test specimen

"Panel of dimensions 50 x 100 cm covered with ceramic tiles 60x120 cm  
marked:  
MAPS OF CERIM WHITE NAT 60x120 RET marchio CERIM"

**Floor test: determination of the anti-slip characteristics:**  
**work areas with high slipping risk.**  
**Procedure for the stamping test inclined plane**  
**(STANDARD DIN 51130:2014)**

The test regards the working areas with a high slipping risk: the procedure foresees that a person taking part in the test walks on a an inclined plane, which is floored with the tested material and greased an oil whose viscosity is SAE 10 W 30.

During the execution of the test it is determined if the tested material may be properly laid down in specific work environments.

There is an average inclination which determines the insecurity of the person walking on the inclined plane and causes the classification of the tested material used to determine the sliding resistance.

**Inclination angle of the inclined plane:** 12,7 °

**Classification:** R 10

**Table with the ratio of the group classification  
and of the inclination degree**

<b>Classification</b>	<b>Inclination angle</b>
n.c. (not classifiable)	lower than 6°
R 9	from 6° to 10°
R 10	over 10° to 19°
R 11	over 19° to 27°
R 12	over 27° to 35°
R 13	over 35°

Mod. P232/1 rev.00



THE DIRECTOR  
(M.L. Simioli)