















## 20,00 mm / FINE PORCELAIN STONEWARE

	Reference standard E.N. 14411-ISO 13006 . Appendix G. Group B1a. UGL	Test method	Reference value	Declared value
	Length and width: admitted deviation, in %, of the average size of each tile from the production dimensions	ISO-10545-2	Squadrato ISO 13006 - $\pm 0,3\%$ ( $\pm 1$ mm)	$\pm 0,15\%$
	Admitted deviation, in %, of the average thickness of each tile from the production dimensions	ISO-10545-2	$\pm 5\%$ ( $\pm 0,5$ mm)	$\pm 5\%$
	Maximum straightness deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	Squadrato ISO 13006 - $\pm 0,3\%$ ( $\pm 0,8$ mm)	$\pm 0,10\%$
	Flatness (centre curvature / edge curvature / warpage)	ISO-10545-2	Squadrato ISO 13006 - $\pm 0,4\%$ ( $\pm 1,8$ mm)	$\pm 0,35\%$
	Surface quality	ISO-10545-2	Il 95% min delle piastrelle deve essere esente da difetti visibili / At least 95% of the tiles must be free from visible flaws / 95% min des carreaux ne doivent présenter aucun défaut visible / Mindestens 95% der Fliesen müssen frei von sichtbaren / mín. el 95% de las baldosas tiene que estar exento de defectos visibles	CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / COOTBETCTBYET
	Maximum right-angle deviation, in %, in relation to the corresponding production dimensions	ISO10545-2	$\pm 0,3\%$ ( $\pm 1,5$ mm)	$\pm 0,20\%$
	Amount of water absorbed, in percentage	ISO-10545-3	$E \leq 0,5\%$	average value 0,08%
	Breaking strength in N (thickness $\geq 7,5$ mm)	ISO-10545-4	$\geq 1300$ Newton	average value 14000 N
	Bending strength in N/mm <sup>2</sup>	ISO-10545-4	$> 35$ N/mm <sup>2</sup>	average value 52 N/mm <sup>2</sup>
	Resistance to deep abrasion of unglazed tiles	ISO-10545-6	$< 175$ mm <sup>3</sup>	average value 140 mm <sup>3</sup>
	Resistance to staining	ISO-10545-14	-	Cl. 4-5
	Thermal shock resistance	ISO-10545-9	-	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	ULA

	Resistance to domestic chemicals and additives for swimming pools	ISO-10545-13	UB minimo / UB minimum / UB minimum / UB mindestens / UB minimo	UA
	Frost resistance	ISO-10545-12	Richiesta / Required / Requisite / Gefordert / Requerida	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Pendulum friction test	BS-7976	-	>36 wet
	Slip resistance with shoes	DIN-51130:2010	-	R11
	Barefoot slip resistance	DIN-51097	-	Cl. C
	Dynamic coefficient of friction (section 9.6 ANSI A 137.1 2012)	DCOF	>0,42 wet	>0,42 wet

**Notes:**







For optimal installation results, Florim recommends maintaining a joint of 2 mm 1/12" for single format installations and 3 mm 1/8" to combine mixed formats.










Copyright © 2013 Florim S.p.A. SB a socio unico.  
Sede Legale: Via Canaletto 24, 41042 Fiorano Modenese.  
Reg. Imprese di Modena Nr. 01265320364.  
Capitale Sociale i.v. Euro 50.000.000 P.I./CF 01265320364

# FLORIM

**Cerim / Match-Up**

## 10,00 mm / FINE PORCELAIN STONEWARE

	Reference standard E.N. 14411-ISO 13006 . Appendix G. Group BIa. UGL	Test method	Reference value	Declared value
	Length and width: admitted deviation, in %, of the average size of each tile from the production dimensions	ISO-10545-2	Squadro ISO 13006 - ±0,3% (±1 mm)	±0,15%
	Admitted deviation, in %, of the average thickness of each tile from the production dimensions	ISO-10545-2	±5% (±0,5 mm)	±5%
	Maximum straightness deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	Squadro ISO 13006 - ±0,3% (±0,8 mm)	±0,10%
	Flatness (centre curvature / edge curvature / warpage)	ISO-10545-2	Squadro ISO 13006 - ±0,4% (±1,8 mm)	±0,35%
	Surface quality	ISO-10545-2	Il 95% min delle piastrelle deve essere esente da difetti visibili / At least 95% of the tiles must be free from visible flaws / 95% min des carreaux ne doivent présenter aucun défaut visible / Mindestens 95% der Fliesen müssen frei von sichtbaren / mín. el 95% de las baldosas tiene que estar exento de defectos visibles	CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / COOTBETCTBYET
	Maximum right-angle deviation, in %, in relation to the corresponding production dimensions	ISO10545-2	±0,3% (±1,5 mm)	±0,20%

	Amount of water absorbed, in percentage	ISO-10545-3	E≤0,5%	average value 0,08%
	Breaking strength in N (thickness ≥ 7,5 mm)	ISO-10545-4	≥1300 Newton	average value 3200 N
	Bending strength in N/mm2	ISO-10545-4	>35 N/mm2	average value 50 N/mm2
	Resistance to deep abrasion of unglazed tiles	ISO-10545-6	<175 mm3	average value 140 mm3
	Resistance to staining	ISO-10545-14	-	Cl. 4-5 GRIP
	Resistance to staining	ISO-10545-14	-	Cl. 5 COMFORT
	Thermal shock resistance	ISO-10545-9	-	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	ULA
	Resistance to domestic chemicals and additives for swimming pools	ISO-10545-13	UB minimo / UB minimum / UB minimum / UB mindestens / UB minimo	UA
	Frost resistance	ISO-10545-12	Richiesta / Required / Requisite / Gefordert / Requerida	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Pendulum friction test	BS-7976	-	>36 wet
	Slip resistance with shoes	DIN-51130:2010	-	R11 GRIP
	Slip resistance with shoes	DIN-51130:2010	-	R10 COMFORT
	Barefoot slip resistance	DIN-51097	-	Cl. B



Dynamic coefficient of friction (section 9.6 ANSI A 137.1 2012) DCOF

&gt;0,42 wet

&gt;0,42 wet

**Notes:**

For optimal installation results, Florim recommends maintaining a joint of 2 mm 1/12" for single format installations and 3 mm 1/8" to combine mixed formats.












Copyright © 2013 Florim S.p.A. SB a socio unico.  
Sede Legale: Via Canaletto 24, 41042 Fiorano Modenese.  
Reg. Imprese di Modena Nr. 01265320364.  
Capitale Sociale i.v. Euro 50.000.000 P/CF 01265320364

# FLORIM

Cerim / Match-Up

**6,00 mm / FINE PORCELAIN STONEWARE**

	Reference standard E.N. 14411-ISO 13006 . Appendix G. Group Bla. UGL	Test method	Reference value	Declared value
	Length and width: admitted deviation, in %, of the average size of each tile from the production dimensions	ISO-10545-2	Squadrate ISO 13006 - $\pm 0,3\%$ ( $\pm 1$ mm)	$\pm 0,15\%$
	Admitted deviation, in %, of the average thickness of each tile from the production dimensions	ISO-10545-2	$\pm 5\%$ ( $\pm 0,5$ mm)	$\pm 5\%$
	Maximum straightness deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	Squadrate ISO 13006 - $\pm 0,3\%$ ( $\pm 0,8$ mm)	$\pm 0,10\%$
	Flatness (centre curvature / edge curvature / warpage)	ISO-10545-2	Squadrate ISO 13006 - $\pm 0,4\%$ ( $\pm 1,8$ mm)	$\pm 0,2\%$
	Surface quality	ISO-10545-2	Il 95% min delle piastrelle deve essere esente da difetti visibili / At least 95% of the tiles must be free from visible flaws / 95% min des carreaux ne doivent présenter aucun défaut visible / Mindestens 95% der Fliesen müssen frei von sichtbaren / min. el 95% de las baldosas tiene que estar exento de defectos visibles	CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / COOTBETCTBYET
	Maximum right-angle deviation, in %, in relation to the corresponding production dimensions	ISO10545-2	$\pm 0,3\%$ ( $\pm 1,5$ mm)	$\pm 0,20\%$
	Amount of water absorbed, in percentage	ISO-10545-3	$E \leq 0,5\%$	average value 0,08%
	Breaking strength in N (thickness < 7,5 mm)	ISO-10545-4	$\geq 700$ Newton	average value 1350 N
	Bending strength in N/mm <sup>2</sup>	ISO-10545-4	$> 35$ N/mm <sup>2</sup>	average value 52 N/mm <sup>2</sup>
	Resistance to deep abrasion of unglazed tiles	ISO-10545-6	$< 175$ mm <sup>3</sup>	average value 140 mm <sup>3</sup>
	Resistance to staining	ISO-10545-14	-	Cl. 4-5 GLOSSY

	Resistance to staining	ISO-10545-14	-	Cl. 5 COMFORT
	Thermal shock resistance	ISO-10545-9	-	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	ULA COMFORT
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	ULA-ULB GLOSSY
	Resistance to domestic chemicals and additives for swimming pools	ISO-10545-13	UB minimo / UB minimum / UB minimum / UB mindestens / UB minimo	UA
	Frost resistance	ISO-10545-12	Richiesta / Required / Requisite / Gefordert / Requerida	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Release of hazardous substances	DM-1-2-2007-Reg-CE-1935-2004	Valore dichiarato per superfici gl con impieghi su piani di lavoro / Declared value for gl surfaces used on worktops / valeur déclarée Pour surfaces gl utilisées sur plans de travail / angegeben wert für Gl oberflächen zum gebrauch als arbeitsplatten / valor declarado Para acabados gl utilizados para superficies de trabajo / заявленное значение для глазурованных поверхностей, с использованием на рабочих столах	CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / COOTBETCTBYET
	Pendulum friction test	BS-7976	-	>36 wet COMFORT
	Slip resistance with shoes	DIN-51130:2010	-	R10 COMFORT
	Barefoot slip resistance	DIN-51097	-	Cl. B COMFORT
	Dynamic coefficient of friction (section 9.6 ANSI A 137.1 2012)	DCOF	>0,42 wet	>0,42 wet

**Notes:**

For optimal installation results, Florim recommends maintaining a joint of 2 mm 1/12" for single format installations and 3 mm 1/8" to combine mixed formats.