



MODENA CENTRO PROVE s.r.l.

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059822417 r.a. - Fax 059380281 - e-mail : info@modenacentroprove.it - www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364


TEST REPORT: 20201958/3

Modena, 26/03/20

CUSTOMER	FLORIM CERAMICHE SPA - - VIA CANALETTO 24 - 41042 - FIORANO MODENESE - MO
MATERIAL and/o SAMPLE to be tested	PORCELAIN TILES;
Denomination	Serie Buildtech 2.0 articolo White CE R+PTV formato 60x60 cm spessore 10 mm marchio Floor gres;
Date of sample reception	07/02/2020;
Kind of test executed	Slip resistance of pedestrian surfaces with Pendulum Testers
Referring standards	BS 7976-2:2002+A1:2013
Shifting from standards	No one
Equipment	Pendulum cod. MCP C163
Subcontracted phases	No one
Sampling made by	Customer

*The test results showing in this Report are only referred to the sample taken by our staff or supplied by the Customer. He commits himself to reproduce integrally this document. Partial reproduction is forbidden.
The times of retain of the samples was indicated in the offer related to the test report.*

Examiner


p.i. Nasseti Luca

MODENA CENTRO PROVE

Ceramic Dept. Responsible
P.I. De Pasquale Roberto

MODENA CENTRO PROVE

Director
Sant'Unione dr. Giuseppe



SLIP RESISTANCE OF PEDESTRIAN SURFACES WITH PENDULUM TESTERS

Beginning date : 18/02/2020

Analysis ending date : 18/02/2020

SAMPLE : sample marked " Serie Buildtech 2.0 articolo White CE R+PTV formato 60x60 cm spessore 10 mm marchio Floor gres "

The friction characteristics of each specimen shall be assessed by determining dynamic friction between the specimen and the slider of a pendulum swinging in a vertical plane.

RESULTS

Rubber used

(hardness): 4S(96)

PTV - DRY TEST

SAMPLE	1	2	3	4	5	Average value
1	55	55	55	55	55	55
2	55	55	55	55	55	55
3	55	55	55	55	55	55
4	55	55	55	55	55	55
5	55	55	55	55	55	55
PTV average value						55

PTV - WET TEST

SAMPLE	1	2	3	4	5	Average value
1	45	45	45	45	45	45
2	45	45	45	45	45	45
3	45	45	45	45	45	45
4	45	45	45	45	45	45
5	45	45	45	45	45	45
PTV average value						45

REFERENCE VALUES – UK Slip Resistance Group Guidelines Issue 5 2016

Classe	PTV (pendulum test value)
High slip potential	0 ÷ 24
Moderate slip potential	25 ÷ 35
Low slip potential	≥ 36

Examiner p.i. Nassetti Luca	MODENA CENTRO PROVE Ceramic Dept. Responsible P.I. De Pasquale Roberto	MODENA CENTRO PROVE Director Sant'Unione dr. Giuseppe
-------------------------------------------	----------------------------------------------------------------------------------	-----------------------------------------------------------------