

|                            |   |                     |  |
|----------------------------|---|---------------------|--|
| <i>Requested by:</i>       | FLORIM CERAMICHE S.p.A. - Via Canaletto 24 – 41042 FIORANO MODENESE (MO)  |                     |  |
| <i>For the sample:</i>     | Ceramic tiles 30 x 30 x 1,0 cm marked "Unglazed ceramic tiles - Brand FLOOR GRES – CHROMTECH 1.0 NAT 30x30 cm". |                     |  |
| <i>On (date):</i> 24/09/15 | <i>Date of receipt in laboratory (sample delivered by the client):</i> 28/09/15                                 |                     |  |
| <i>Test date</i>           | <i>From:</i> 31/09/15   | <i>To:</i> 01/10/15 |  |


**EN ISO 10545-14 – Determination of stain resistance**

| Test solutions                              | Resistance class |                 |                 |                 |                 |
|---|------------------|-----------------|-----------------|-----------------|-----------------|
|   | Test specimen 1  | Test specimen 2 | Test specimen 3 | Test specimen 4 | Test specimen 5 |
| <b>Stains</b>                               |                  |                 |                 |                 |                 |
| Chrome green in light oil                   | 5                | 5               | 5               | 5               | 5               |
| Iodine (alcoholic solution 13g/l)           | 5                | 5               | 5               | 5               | 5               |
| Olive oil (def. Olive Oil Agreement - 1979) | 4                | 4               | 4               | 4               | 4               |

Stain resistance class - References

- Resistance class 1: Stain not removed.
- Resistance class 2: Stain removed by dipping in a suitable solvent for 24 hours.
- Resistance class 3: Stain removed by mechanical cleaning and strong cleansing agent.
- Resistance class 4: Stain removed by manual cleaning with weak cleansing agent .
- Resistance class 5: Stain removed by means of hot current water for 5 min.

Eng. Giordana Carani  
Technical approval



Prof. Maria Chiara Bignozzi  
Director



*The results reported relate only to the samples tested. No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision. The reproduction of this test report is only authorized in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction. This test report consists of 1 pages, this cover included.*