



MODENA CENTRO PROVE s.r.l.

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059 822417 r.a. - Fax 059380281 - e-mail : info@modenacentroprove.it - www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

MECCANICA

ECOLOGIA

CERAMICA

ALIMENTARE



Certificato n°
50 100 4582



Diploma
IWR/IT n°
30438



Socio



Membro



Socio

Unione Industriali
Modena



Iscritto

ASSOCIATO



ASSOCIATED

Modena, 11/12/14

To **FLORIM CERAMICHE SPA**
VIA CANALETTO 24
41042 FIORANO MODENESE MO

Attn. **D. TURRINI**

MATERIAL and/or SAMPLE to be tested : PORCELAIN TILES;

Denomination of the Sample

Articolo: Ivory bocciardato
Serie: Industrial
: Formato : diversi formati
Superficie: UGL
Marchio Floor gres;

Client Reference: Your delivery NS RITIRO

date:

Here attached, you will receive the Test Report of Serial No. **20147403/n**, which shows the results of tests required.

MODENA CENTRO PROVE

MODENA CENTRO PROVE

Director
Sant'Unione dr. Giuseppe



MODENA CENTRO PROVE s.r.l.

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059822417 r.a. - Fax 059380281 - e-mail : info@modenacentroprove.it - www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

TEST REPORT: 20147403/1

Modena, 11/12/14

CUSTOMER	FLORIM CERAMICHE SPA - - VIA CANALETTO 24 - 41042 - FIORANO MODENESE - MO
MATERIAL and/o SAMPLE to be tested	PORCELAIN TILES; Articolo: Ivory bocciardato Serie: Industrial Formato : diversi formati Superficie: UGL Marchio Floor gres;
Denomination	
Date of sample reception	09/12/2014;
Kind of test executed	Determination of Slipperiness
Referring standards	DIN 51097:1992
Shifting from standards	None
Equipment	Pullmeter with ramp cod. MCP C23
Calibration	Taratura n. 08 del 28/04/2014
Subcontracted phases	None
Sampling made by	Customer

*The test results showing in this Report are only referred to the sample taken by our staff or supplied by the Customer. He commits himself to reproduce integrally this document. Partial reproduction is forbidden.
The times of retain of the samples was indicated in the offer related to the test report.*

Examiner

P.I. Fili Thomas
Examiner

P.I. Rebottini Mattia

MODENA CENTRO PROVE

Ceramic Dept. Responsible
P.I. De Pasquale Roberto

MODENA CENTRO PROVE

Director
Sant'Unione dr. Giuseppe

**MODENA CENTRO PROVE s.r.l.**

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059822417 r.a. - Fax 059380281 - e-mail : info@modenacentroprove.it - www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

DETERMINATION OF SLIPPERINESS

Beginning date : 10/12/2014

Analysis ending date : 11/12/2014

SAMPLE : Ceramic tiles marked « Articolo: Ivory bocciardato - Serie: Industrial - Formato : diversi formati - Superficie: UGL - Marchio Floor gres »

A person walks backwards and forwards barefoot across the tiles to be tested, the inclination of which is increased by about 1° per second; the angle of inclination at which the person is no longer in conditions of safety is defined as the slip angle. The surface is wet continuously with a solution (1 g/l of wetting agent + water).

RESULTS

- Sample dimensions (length, width) : 1x 0.5 (m)
- Width of joints : 5 (mm)
- Grout substance : mortar
- D of profiles : none

- SLIP ANGLE : 28,5°
- CLASSIFICATION : C (A+B+C)

CLASSIFICATION

Total Average Values	Group Classification
< 12	0
≥ 12°	A
≥ 18°	B
≥ 24°	C

Examiner
P.I. Fili Thomas**Examiner**

P.I. Rebottini MattiaMODENA CENTRO PROVE

Ceramic Dept. Responsible
P.I. De Pasquale RobertoMODENA CENTRO PROVE

Director
Sant'Unione dr. Giuseppe