



LAB N° 1170

Scandiano, 07/30/2013



Messrs **FLORIM CERAMICHE S.p.a.**

Via Canaletto, 24
41042 FIORANO MODENESE
(MO)

Confidential Test Report N. 2850/2013 /I

on ceramic tiles

Our ref.num.: 10071
Date of request: 07/19/2013

Test Specimen

"Panel of dimensions 50 x 100 cm covered with unglazed ceramic tiles 30x60 cm
marked:
Articolo taupe soft, serie Industrial, formato 30x60, superficie UGL, marchio Floor Gres"

Source

Submitted to Laboratory by Client

Date Received

07/23/2013

Time of test execution

start: 07/29/2013 end: 07/29/2013

Test detail / method description / test procedure

" Determination of the anti-slip characteristics -
Standard DIN 51130:2010 "

*The report relates only to the sample(s) tested. This report must not be reproduced in part
without the written permission of Main Laboratory Sassuolo, nor used in any way as to lead to
misrepresentation of the results or their implications.*

Page 1 of 2

Mod. P232/1 rev.00



LAB N° 1170

Confidential Test Report N. 2850/2013 /I
FLORIM CERAMICHE S.p.a.

Page 2 of 2

Date 07/30/2013

Test specimen

"Panel of dimensions 50 x 100 cm covered with unglazed ceramic tiles 30x60 cm marked:

Articolo taupe soft, serie Industrial, formato 30x60, superficie UGL, marchio Floor Gres"

Floor test: determination of the anti-slip characteristics:
work areas with high slipping risk.
Procedure for the stamping test inclined plane
(STANDARD DIN 51130:2010)

The test regards the working areas with a high slipping risk: the procedure foresees that a person taking part in the test walks on an inclined plane, which is floored with the tested material and greased with an oil whose viscosity is SAE 10 W 30.

During the execution of the test it is determined if the tested material may be properly laid down in specific work environments.

There is an average inclination which determines the insecurity of the person walking on the inclined plane and causes the classification of the tested material used to determine the sliding resistance.

Inclination angle of the inclined plane: 9,4 °

Classification: R 9

**Table with the ratio of the group classification
and of the inclination degree**

Classification	Inclination angle
n.c. (not classifiable)	lower than 6°
R 9	from 6° to 10°
R 10	over 10° to 19°
R 11	over 19° to 27°
R 12	over 27° to 35°
R 13	over 35°

Mod. P232/1 rev.00



THE DIRECTOR
(M.L. Simiotti)