






TEST REPORT: 20180409/2

Modena, 29/01/18

| | |
|---|---|
| CUSTOMER | FLORIM CERAMICHE SPA - - VIA CANALETTO 24 - 41042 - FIORANO MODENESE - MO |
| MATERIAL and/o SAMPLE to be tested | porcelain tiles; |
| Denomination | Serie: Prexious of Rex Articolo: Charming amber Formato: 60x60 Spessore: 10 mm Marchio : Rex; |
| Date of sample reception | 10/01/2018; |
| Date of sample acceptance | 16/01/2018; |
| Kind of test executed | Determination of Crazing Resistance |
| Referring standards | UNI EN ISO 10545-11:2000 |
| Shifting from standards | None |
| Equipment | Autoclave cod. MCP C58 |
| Calibration | RT 13 of 20-06-2017 |
| Subcontracted phases | None |
| Sampling made by | Customer |

*The test results showing in this Report are only referred to the sample taken by our staff or supplied by the Customer. He commits himself to reproduce integrally this document. Partial reproduction is forbidden.
The times of retain of the samples was indicated in the offer related to the test report.*

| | | |
|--|---|--|
|  p.l. Bortolai Alberto |  MODENA CENTRO PROVE Ceramic Dept. Responsible P.I. De Pasquale Roberto |  MODENA CENTRO PROVE Director Sant'Unione dr. Giuseppe |
|--|---|--|



MODENA CENTRO PROVE s.r.l.
Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059 822417 r.a. - Fax 059380281 -
e-mail : info@modenacentroprove.it - www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

DETERMINATION OF CRAZING RESISTANCE

Beginning date : 22/01/2018

Analysis ending date : 23/01/2018

SAMPLE : Ceramic tiles, marked « **Serie: Prexious of Rex Articolo: Charming amber Formato: 60x60 Spessore: 10 mm Marchio : Rex** »

The test was performed by subjecting whole tiles in an autoclave in order to maintain a pressure of 500 KPa for 2 h.

RESULTS

- Number of test specimens : 5
- Number of test specimens showing crazing : 0
- Description of crazing : none


REQUIREMENTS

(Norm UNI EN 14411:2016 Annex G)

No ceramic tiles must present visible defects.

Examiner


p.l. Bortolai Alberto

MODENA CENTRO PROVE

Ceramic Dept. Responsible
P.I. De Pasquale Roberto

MODENA CENTRO PROVE

Director
Sant'Unione dr. Giuseppe