



MODENA CENTRO PROVE s.r.l.

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059822417 r.a. - Fax 059380281 - e-mail : info@modenacentroprove.it - www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

TEST REPORT: 20123166/2


Modena, 17/07/12


CUSTOMER	FLORIM CERAMICHE SPA - - VIA CANALETTO 24 - 41042 - FIORANO MODENESE - MO
MATERIAL and/o SAMPLE to be tested	UNGLAZED CERAMIC TILES;
Denomination	SERIE SELECTION OAK MARCHIO REX ARTICOLO WHITE GRIP;
Date of sample reception	06/07/2012;
Kind of test executed	Determination of Slipperiness
Referring standards	DIN 51097:1992
Shifting from standards	None
Equipment	Scivolosimetro (misuratore del grado critico di inclinazione) cod. MCP C23
Calibration	Taratura n. 06 del 28/04/2012
Subcontracted phases	None
Sampling made by	Customer

*The test results showing in this Report are only referred to the sample taken by our staff or supplied by the Customer. He commits himself to reproduce integrally this document. Partial reproduction is forbidden.
The times of retain of the samples was indicated in the offer related to the test report.*

Examiner


P.I. Fili Thomas

Examiner

P.I. Rebutini Maria

MODENA CENTRO PROVE

Ceramic Dept. Responsible
P.I. De Pasquale Roberto

MODENA CENTRO PROVE

Director
Sant'Unione dr. Giuseppe

**MODENA CENTRO PROVE s.r.l.**

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059822417 r.a. - Fax 059380281 - e-mail : info@modenacentroprove.it - www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

DETERMINATION OF SLIPPERINESS

Beginning date : 10/07/2012

Analysis ending date : 12/07/2012

SAMPLE : Ceramic tiles, marked « SERIE SELECTION OAK MARCHIO REX ARTICOLO WHITE GRIP »

A person walks backwards and forwards barefoot across the tiles to be tested, the inclination of which is increased by about 1° per second; the angle of inclination at which the person is no longer in conditions of safety is defined as the slip angle. The surface is wet continuously with a solution (1 g/l of wetting agent + water).

RESULTS

- Sample dimensions (length, width) : 1x 0.5 (m)
- Width of joints : 5 (mm)
- Groutig substance : mortar
- D of profiles : none

- SLIP ANGLE : 26,3°
- CLASSIFICATION : A+B+C

CLASSIFICATION

Total Average Values	Group Classification
< 12	0
≥ 12°	A
≥ 18°	B
≥ 24°	C

Examiner
P.I. Fili Thomas**Examiner**
P.I. Rebottini Matia**MODENA CENTRO PROVE**

Ceramic Dept. Responsible
P.I. De Pasquale Roberto**MODENA CENTRO PROVE**

Director
Sant'Unione dr. Giuseppe