






















10,00 mm / FINE PORCELAIN STONEWARE

	Reference standard E.N. 14411 . Appendix G. Group Bla. UGL	Test method	Reference value	Declared value
	Length and width: admitted deviation, in %, of the average size of each tile from the production dimensions	ISO-10545-2	±0,6% (±2 mm)	± 0,15%
	Admitted deviation, in %, of the average thickness of each tile from the production dimensions	ISO-10545-2	±5% (±0,5 mm)	± 5%
	Maximum straightness deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	±0,5% (±1,5 mm)	± 0,1%
	Maximum right-angle deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	±0,5% (±2 mm)	± 0,2%
	Flatness (centre curvature / edge curvature / warpage)	ISO-10545-2	±0,5% (±2mm)	± 0,35%
	Surface quality	ISO-10545-2	Il 95% min delle piastrelle deve essere esente da difetti visibili / At least 95% of the tiles must be free from visible flaws / 95% min des carreaux ne doivent présenter aucun défaut visible / Mindestens 95% der Fliesen müssen frei von sichtbaren / mín. el 95% de las baldosas tiene que estar exento de defectos visibles	CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / COOTBETCTBYET
	Amount of water absorbed, in percentage	ISO-10545-3	E<0,5%	average value 0,08%
	Breaking strength in N (thickness >= 7,5 mm)	ISO-10545-4	≥1300 Newton	average value 3200 N
	Bending strength in N/mm2	ISO-10545-4	>35 N/mm2	average value 50 N/mm2
	Resistance to deep abrasion of unglazed tiles	ISO-10545-6	<175 mm3	average value 140
	Thermal shock resistance	ISO-10545-9	-	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Frost resistance	ISO-10545-12	Richiesta / Required / Requisite / Gefordert / Requerida	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	ULA

	Resistance to domestic chemicals and additives for swimming pools	ISO-10545-13	UB minimo / UB minimum / UB minimum / UB mindestens / UB minimo	UA
	Resistance to staining	ISO-10545-14	-	Cl. 4
	Slip resistance with shoes	DIN-51130:2010	-	R9 MATTE
	Slip resistance with shoes	DIN-51130:2010	-	R11 SLATE-HAMMERED
	Slip resistance with shoes	DIN-51130:2010	-	R10
	Barefoot slip resistance	DIN-51097	-	Cl. C SLATE-HAMMERED
	Static coefficient of friction	ASTM-C1028	>0,60 dry and wet	> 0,6 dry and wet
	Dynamic coefficient of friction (section 9.6 ANSI A 137.1 2012)	DCOF	>0,42 wet	> 0,42 wet

Notes:





For optimal installation results, Florim recommends maintaining a joint of 2 mm 1/12" for single format installations and 3 mm 1/8" to combine mixed formats.














Copyright © 2013 Florim Ceramiche S.P.A. a socio unico.
Sede Legale: Via Canaletto 24, 41042 Fiorano Modenese.
Reg. Imprese di Modena Nr. 01265320364.
Capitale Sociale i.v. Euro 50.000.000 P.I./CF 01265320364

FLORIM

Rex / Selection Oak

20,00 mm / FINE PORCELAIN STONEWARE

	Reference standard E.N. 14411 . Appendix G. Group Bia. UGL	Test method	Reference value	Declared value
	Length and width: admitted deviation, in %, of the average size of each tile from the production dimensions	ISO-10545-2	±0,6% (±2 mm)	± 0,15%
	Admitted deviation, in %, of the average thickness of each tile from the production dimensions	ISO-10545-2	±5% (±0,5 mm)	± 5%
	Maximum straightness deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	±0,5% (±1,5 mm)	± 0,1%
	Maximum right-angle deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	±0,5% (±2 mm)	± 0,2%

	Surface quality	ISO-10545-2	Il 95% min delle piastrelle deve essere esente da difetti visibili / At least 95% of the tiles must be free from visible flaws / 95% min des carreaux ne doivent présenter aucun défaut visible / Mindestens 95% der Fliesen müssen frei von sichtbaren / min. el 95% de las baldosas tiene que estar exento de defectos visibles	CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / COOTBETCTBYET
	Amount of water absorbed, in percentage	ISO-10545-3	E<0,5%	average value 0,08%
	Breaking strength in N (thickness >= 7,5 mm)	ISO-10545-4	≥1300 Newton	average value 14000 N
	Bending strength in N/mm2	ISO-10545-4	>35 N/mm2	average value 52 N/mm2
	Resistance to deep abrasion of unglazed tiles	ISO-10545-6	<175 mm3	average value 140
	Thermal shock resistance	ISO-10545-9	-	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Frost resistance	ISO-10545-12	Richiesta / Required / Requisite / Gefordert / Requerida	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	ULA
	Resistance to domestic chemicals and additives for swimming pools	ISO-10545-13	UB minimo / UB minimum / UB minimum / UB mindestens / UB minimo	UA
	Resistance to high concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	UHA
	Slip resistance with shoes	DIN-51130:2010	-	R11
	Barefoot slip resistance	DIN-51097	-	Cl. A+B
	Dynamic coefficient of friction (section 9.6 ANSI A 137.1 2012)	DCOF	>0,42 wet	> 0,42 wet

Notes:

For optimal installation results, Florim recommends maintaining a joint of 2 mm 1/12" for single format installations and 3 mm 1/8" to combine mixed formats.

Ceramic tiles undergo a compacting thermal treatment that ensures resistance and durability. The low level of water absorption makes the slabs frost resistant. This could result in superficial water stagnations even if materials are installed in a workmanlike manner.

