









**10,00 mm / GLAZED PORCELAIN STONEWARE**

| | Reference standard E.N. 14411 . Appendix G. Group B1a. GL | Test method | Reference value | Declared value |
|-------------------------------------------------------------------------------------|-----------------------------------------------------------|-------------|-----------------|--------------------------------------------------|
|  | Surface abrasion | ASTM-C1027 | - | IV (White and Grey); III (Multicolor and Timber) |
|  | Water absorption | ASTM-C373 | - | ≤ 0.5% |
|  | Chemical resistance | ASTM-650 | - | NOT AFFECTED |
|  | Dynamic coefficient of friction | ANSI-137-1 | - | ≥ 0.50 |
|  | Stain Resistance | ASTM-C1378 | - | NOT AFFECTED |
|  | Breaking strength | ASTM-C648 | - | ≥ 400 |
|  | Resistance to freeze | ASTM-C1026 | - | RESISTANT |
|  | Scratch hardness | MOHS | - | ≥ 6 |