










**10,00 mm / GLAZED PORCELAIN STONEWARE**

	Reference standard E.N. 14411 . Appendix G. Group BIa. GL	Test method	Reference value	Declared value
	Surface abrasion	ASTM-C1027	-	IV MATTE
	Surface abrasion	ASTM-C1027	-	V GRIP
	Water absorption	ASTM-C373	-	≤ 0.5%
	Chemical resistance	ASTM-650	-	NOT AFFECTED
	Dynamic coefficient of friction	ANSI-137-1	-	≥ 0.50
	Stain Resistance	ASTM-C1378	-	NOT AFFECTED
	Breaking strength	ASTM-C648	-	≥ 400
	Resistance to freeze	ASTM-C1026	-	RESISTANT
	Scratch hardness	MOHS	-	≥ 7