





















**8,00 mm / COLOURED BODY PORCELAIN STONEWARE**

	Reference standard E.N. 14411 . Appendix G. Group Bla. GL	Test method	Reference value	Declared value
	Surface abrasion	ASTM-C1027	-	III (Nutmeg, Nero)
	Surface abrasion	ASTM-C1027	-	IV
	Water absorption	ASTM-C373	-	≤ 0.5%
	Chemical resistance	ASTM-650	-	CLASS A
	Dynamic coefficient of friction	ANSI-137-1	-	≥ 0.42* MATTE
	Dynamic coefficient of friction	ANSI-137-1	-	≥ 0.35* SEMIPOLISHED
	Stain Resistance	ASTM-C1378	-	CLASS A
	Breaking strength	ASTM-C648	-	> 400 (9mm), > 300 (8mm)
	Resistance to freeze	ASTM-C1026	-	RESISTANT
	Scratch hardness	MOHS	-	≥ 7

Copyright © 2013 Florim Ceramiche S.P.A. a socio unico.
Sede Legale: Via Canaletto 24, 41042 Fiorano Modenese.
Reg. Imprese di Modena Nr. 01265320364.
Capitale Sociale i.v. Euro 50.000.000 PI/CF 01265320364

**10,00 mm / COLOURED BODY PORCELAIN STONEWARE**

	Reference standard E.N. 14411 . Appendix G. Group Bla. GL	Test method	Reference value	Declared value
	Surface abrasion	ASTM-C1027	-	III (Nutmeg, Nero)

	Surface abrasion	ASTM-C1027	-	IV
	Water absorption	ASTM-C373	-	≤ 0.5%
	Chemical resistance	ASTM-650	-	CLASS A
	Dynamic coefficient of friction	ANSI-137-1	-	≥ 0.42* MATTE
	Dynamic coefficient of friction	ANSI-137-1	-	≥ 0.35* SEMIPOLISHED
	Stain Resistance	ASTM-C1378	-	CLASS A
	Breaking strength	ASTM-C648	-	> 400 (9mm), > 300 (8mm)
	Resistance to freeze	ASTM-C1026	-	RESISTANT
	Scratch hardness	MOHS	-	≥ 7