







**9,00 mm / GLAZED PORCELAIN STONEWARE**

	Reference standard E.N. 14411 . Appendix G. Group BIa. GL	Test method	Reference value	Declared value
	Surface abrasion	ASTM-C1027	-	IV
	Water absorption	ASTM-C373	-	≤ 0.5%
	Chemical resistance	ASTM-650	-	CLASS A
	Breaking strength	ASTM-C648	-	> 400 (9mm), > 300 (8mm)
	Resistance to freeze	ASTM-C1026	-	RESISTANT
	Scratch hardness	MOHS	-	≥ 7